



Date of Issue: 8/24/2022
Report Number: 22-002427
Revision Number: 2
Date Order Received: 07/19/2022

For the Account of: Gabriel A/S
Hjulmagervej 55
9000 Aalborg Denmark

Client's Identification: Focus Royal Col 60512

CERTIFICATE OF TESTING

TEST PERFORMED: Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D 4034-92

TEST RESULTS

Specimen	Warp Yarn Slippage (lbf)	Type of Failure	Specimen	Fill Yarn Slippage (lbf)	Type of Failure
1	33.9	SS	1	32.4	SS
2	40.8	SS	2	36.2	SS
3	36.2	SS	3	40.1	SS
4	30.1	SS	4	30.6	SS
5	33.8	SS	5	32.8	SS
Avg. Warp	35.0		Avg. Fill	34.5	

ABBREVIATIONS USED

- SB** Seam broke before 1/4" slippage - Results should reflect this
SS 1/4" slippage occurred - Note: Actual slippage of yarns is visible
FB Fabric broke before 1/4" slippage - Note: Actual breakage is visible

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine

Seam Description:

Seam Type	Standard Lockstitch
Stitches per Inch	7 ± 0.5 stitches per inch
Needle Used	Size 22 NM: 140, 135x17 ball point needle
Thread	Nymo EX Bonded Nylon thread; 5x is used for the bobbin and 8x is used for the needle

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	25 lbs. Minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Jillian Matice

Authorized Signature

Date Order Completed: 07/22/2022