



Date of Issue: 9/16/2022 Report Number: 22-003021

Revision Number:1

Date Order Received: 09/12/2022

For the Account of:

Gabriel A/S

Hjulmagervej 55

9000 Aalborg Denmark

Client's Iden	tification:	Foo	us Royal COL 60509		
			CEDTIFICAT	E OF TESTING	
TEOT DEDE	ODMED: A				
TEST PERF	ORMED: A	ibrasion Res	istance of Textile Fabrics (Mart	indale Abrasion Tester Method) ASTM D4966-12E1	
EST RESULTS	3				
Specim		en Number of Cycles		Rating	
1			50,000	Breakage occurred	
2			50,000	Breakage occurred	
3			50,000	Breakage occurred	
INTEDDDETA	TION LISED				
INTERPRETATION USED Solution 1 The end point is read			is no solved on a consum falseis color	no torre an manual reason have breaken an an a location of fabric reason a bala	
E Option i		The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.			
☐ Opti	Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.				
NOTES					
Test Conditions:		70 ±4°F, 65 ±5% Relative Humidity			
Sampling Method:		As Received			
Abradant Used:		Worsted Wool Standard Abradant Fabric			
Weight:		12 ± 0.3 kPa			
Foam Backing Used:		☐ No			
Approximate Weight					
Of Fabric:		13.5 ounces / square yard			
ACCEPTANC	E CRITERIA	١			
A.C.T. Standa			Acceptance Criteria		
General Contract Uphols		, , , , , , , , , , , , , , , , , , , ,		·	
Heavy Duty U	pholstery		No appreciable breakage or wea	r after 40,000 cycles	
CONCLUSION	ON Based on the above Results and the A.C.T. Standard, the item tested:			, the item tested:	
	□ Ui	□ Unrated			
	□G	General Contract Upholstery			
	X H	☑ Heavy Duty Upholstery			
CERTIFICATION Specified by the	-			g specimen in accordance with the procedures and equipment	
Berta S	Stiven				
Authorized Sign				Date Order Completed: 09/16/2022	

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1